



Southwestern Sales Company  
Rogers, Arkansas 72757-1257  
800-427-9368 fax 479-636-4718  
www tarpARMOR.com

---

August 6, 2012

Mr. Don Curran  
Board Member  
State Marketing Board for Recyclables  
5301 Northshore Dr.  
North Little Rock, AR 72118-5317

Dear Mr. Curran:

Thank you for contacting me regarding helping find an outlet for the secondary material my company is generating. On average, we currently dispose of 4 to 5 tons of LDPE-coated HDPE sheeting every 12 days (one 40 cubic yard roll-off container).

Enclosed you will find samples of the material. The material is in loose form in Rogers, AR.

Please let me know if you have any leads for anyone who may have an interest in this material. Unfortunately, it is currently going into the landfill.

Thank you for your assistance.

Best regards,

A handwritten signature in black ink that reads "Shannon Harrop". The signature is written in a cursive, flowing style.

Shannon Harrop  
Operations Manager  
Southwestern Sales Co.



**Southwestern Sales Company**

P.O. Box 1257  
Rogers, AR 72757-1257  
www.swsalesco.com

479-636-6943  
800-636-1975  
FAX: 479-636-4718

**POLYLITE® SUPER**

(SU 10X10)

**PHYSICAL CHARACTERISTICS**

- Color ..... UV Clear
- Construction..... HDPE 1000 Denier + or - 10%  
Natural, UV 10X10 Counts per  
inch in warp and fill.
- Coating..... LDPE 1 1/2 Mils each side (+ or - 10%)
- Thickness ..... 6 1/2 Mils + or - 10%
- Weight/Sq Yd ..... 4.2oz./sq.yd. (+ or - 10%)  
(ASTI D - 1910 Garb)
- Tensile Strength ..... 133.5 lbs. Warp - 125.5 lbs. Fill  
(ASTI D-1682, Garb)
- Tear Strength ..... 6,400 grams Warp - 6,400 grams  
Fill (ASTI D - 1424 Elmendorf)
- Burst Strength..... 200.0 P.S.I. (ASTI D - 751  
Mullen)
- U.V. .... More than 80% ASTM G 53-84  
strength retention after 2000 hours

UV → CIBA  
944

**NOTE:** These typical property values are intended as guides only, and not as specification limits.



**POLYLITE®TITAN**  
**CLEAR**

(TI 14x14)

**PHYSICAL CHARACTERISTICS**

- Color ..... UV Clear
- Construction..... HDPE 1300 Denier (+/- 10%)  
14 X 14 yarns/inch, UV stabilized  
CIBA 944
- Coating..... LDPE 2 mil each side (+/- 10%)
- Thickness ..... 16 mils (+/-10%) (ASTM D-1777)
- Weight..... 7.5oz per sq.yd. (254 g/m2)  
(+/- 10%) (ASTM D-3776)
- Tensile Strength ..... 251 lbs. Warp (ASTM D-5034)  
230 lbs. Weft
- Tear Strength ..... 56 lbs. Warp (ASTM D-2261)  
50 lbs. Weft
- U.V. .... More than 80% ASTM G 53-84  
strength retention after 2000 hours

**NOTE:** These typical property values are intended as guides only, and not as specification limits.



2A

**POLYLITE® PREMIUM**  
**BLACK, BLACK/WHITE**

(BWP 10X10)

**PHYSICAL CHARACTERISTICS**

Construction.....	Nominal 10 X 10 tape/inch. 850 Denier tapes, Black color, <u>UV</u> stabilized of <u>HDPE</u>	CIBA 944
Coating.....	2 mil average on one side, White Color, <u>UV</u> stabilized, <u>LDPE</u> 2.8 mil average on other side, Black color UV stabilized, LDPE	
Thickness .....	11 mils	
Weight.....	6 oz per square yard (200 gsm2) +/- 10%	
Tensile Strength .....	185 lbs. Warp    ASTM D 5034-95 150 lbs. Weft    (Grab Method: 2")	
Tear Strength .....	36 lbs. Warp    ASTM D 751 33 lbs. Weft	
Weathering..... (Q.UV Test)	More than 80% ASTM G 53-84 strength retention after 2000 hours	

**NOTE:** These typical property values are intended as guides only, and not as specification limits.